

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<p>(51) International Patent Classification ⁷ : C08F 291/18, B01D 67/00, C08F 259/08, 259/02, 255/02</p>	<p>A1</p>	<p>(11) International Publication Number: WO 00/15679</p> <p>(43) International Publication Date: 23 March 2000 (23.03.00)</p>
<p>(21) International Application Number: PCT/GB99/02868</p> <p>(22) International Filing Date: 1 September 1999 (01.09.99)</p> <p>(30) Priority Data: 09/153,458 15 September 1998 (15.09.98) US</p> <p>(71) Applicant (<i>for all designated States except US</i>): NATIONAL POWER PLC [GB/GB]; Windmill Hill Business Park, Whitehill Way, Swindon, Wiltshire SN5 6PB (GB).</p> <p>(72) Inventors; and (75) Inventors/Applicants (<i>for US only</i>): D'AGOSTINO, Vincent, F. [US/US]; 2 Deanne Court, Dix Hills, NY 11746 (US). NEWTON, John, Michael [GB/GB]; Thornwood, Devizes Road, Box, Nr Corsham, Wiltshire SN13 8EG (GB).</p> <p>(74) Agent: BOULT WADE TENNANT; 27 Furnival Street, London EC4A 1PQ (GB).</p>		<p>(81) Designated States: AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, DE, DK, DM, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).</p> <p>Published <i>With international search report.</i></p>
<p>(54) Title: WATER BASED GRAFTING</p> <p>(57) Abstract</p> <p>A process for the preparation of a monomer-grafted cross-linked polymer comprising the steps of: i) activating the polymer by irradiation; ii) quenching the activated polymer so as to effect cross-linking therein; iii) activating the cross-linked polymer by irradiation; iv) contacting the activated cross-linked polymer with an emulsion which comprises: a) an unsaturated monomer; b) an emulsifier; and c) water, for a time sufficient to effect the desired extent of grafting.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon			PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

- 1 -

Water based grafting

The present invention relates to a process for the grafting of an unsaturated monomer to a polymer, in particular to a fluorinated polymer. In particular the present invention relates to a process for forming monomer-grafted cross-linked polymer membranes which may be used as non-ionic exchange membranes or ion-selective exchange membranes. These membranes can be used in various applications such as electrodialysis, dialysis, Donnan dialysis and energy systems such as batteries, redox cells and fuel cells. The present invention may also be applied to the preparation of grafted microporous cross-linked polymer structures. It may also be used to graft different form factors such as threads, non-woven fabrics, tubes, powders, pellets, sheets and/or films.

Techniques for the grafting of an unsaturated monomer to a polymer are described in US Patent Nos 3481848, 4012303, 4339473, 4605685 and 5743940, EP Patent No 0526203 and GB Patent No 1237293. The techniques known in the art all involve the steps of activation of the polymer, i.e. the generation of free radicals on the polymer backbone, and reaction between the activated polymer and the unsaturated monomer to produce a monomer-grafted polymer. These steps may be carried out either simultaneously or sequentially. A review of the subject area is presented in a paper written by B. Gupta and G.G. Scherer, *Chimia* 48 (1994), 127-137.

US-A-3481848 discloses a method of radiation graft polymerization of vinyl compounds onto cellulose in which cellulose is pre-irradiated in air then reacted with a vinyl monomer in an emulsified system and in

which alumina or an alumina-silica mixture is used as a catalyst in order to deactivate OH radicals. Without the catalyst a large quantity of homopolymer is formed. The method is only applied to cellulose membranes and
5 indeed would be unsuitable for many polymers, especially fluorinated polymers, which will undergo degradation and mechanical breakdown if irradiated in air.

US-A-4012303 discloses a process for the simultaneous
10 irradiation grafting of trifluorostyrene to an inert polymeric film base. In this case the polymer is activated by irradiation whilst immersed in an organic solution of the monomer. This process suffers from a number of disadvantages. Firstly, the monomer may
15 undergo significant homopolymerization in preference to being grafted to the polymeric film base since it too is irradiated, and therefore activated, simultaneously with the polymeric film base. Secondly, the process utilises an organic solvent to solubilize the monomer and this is
20 disadvantageous for environmental reasons. Thirdly, the process utilises gamma radiation which, because of its low energy density, requires long radiation times to achieve the required dose. Finally, the process is slow, requiring up to 400 hours to achieve graft levels of
25 about 30%.

US-A-4339473 also discloses a simultaneous radiation grafting process which uses water as the solvent and includes homo- and/or co-polymerisation retardants.
30 Thus, the problem of homopolymerisation is reduced and the use of organic solvents is avoided. However this process is limited to grafting monomers which are hydrophilic, that is monomers which are substantially soluble in water.

- 3 -

US-A-4605685 discloses a sequential process for the irradiation grafting of trifluorostyrene to an inert polymeric film base. This process involves activation of the polymeric film base by irradiation with beta radiation prior to contact with the monomer. If stored at sufficiently low temperatures, the activated polymeric film base may remain stable for up to two months. In this method the monomer solution is not exposed to radiation and this alleviates the problem of homopolymerization of the monomer. However it still retains the disadvantage of the use of organic solvents to solubilize the monomer and, although faster than the simultaneous grafting process of US-A-4012303, it still requires lengthy reaction times for the grafting step, typically about 20 hours at 50 degC. The reaction time may be lowered by the removal of the radical inhibitors which are commonly added to commercially available unsaturated monomers to increase their shelf life. However this is a costly and time-consuming process. Furthermore, the percentage graft, even at such long reaction times, is still only about 50% at most.

US-A-5743940 also discloses a sequential process in which an organic high molecular weight compound is exposed to an ionising radiation and thereafter a polymerisable monomer that either contains ion exchange groups or a polymerisable monomer that can be converted to provide ion-exchange groups is incorporated in the irradiated compound by graft polymerization. The monomer may be incorporated by liquid- or vapour-phase graft polymerization but the former is presumably only possible in aqueous solution when the polymerisable monomer is water soluble.

GB-A-1237293 discloses the use of an emulsion of a

- 4 -

monomer in water for grafting to a polymer by thermal polymerization. The process involves simultaneous thermal activation of the polymer and reaction with an emulsion of the monomer in water. Although the disclosure makes no mention of homopolymerization, it is highly likely to be a problem for such a process where the polymer and monomer are subjected to thermal activation at the same time. Presumably, in order to alleviate the problem of homopolymerization the process operates at very low concentrations of monomer resulting in only low levels of grafting.

EP-A-0526203 discloses a separation membrane composed of microporous polyethylene having fine pores substantially filled with a graft polymer. The membrane is obtained by bringing microporous polyethylene having radicals formed by plasma irradiation into contact with an emulsion comprising a water-insoluble monomer, a surface-active agent and water.

It is an object of the present invention to provide a process for cross-linking a polymer and grafting a monomer thereto which does not require the use of an organic solvent and which does not result in significant homopolymerization of the monomer but which provides a uniform graft of a monomer throughout a polymer within a reasonable reaction time at a low reaction temperature.

Cross-linking, also known in the art as "reticulation", generally improves the physical properties of the polymer. It creates a more tightly structured polymer which has a higher glass transition temperature and in which other physical properties such as tensile strength, refractive index, creep, compression set and

stress relaxation are also improved. Improvements in such physical properties are particularly advantageous when the polymer is used to produce a thin film such as is required when forming an ion-exchange membrane.

5 Cross-linking also generally reduces the chemical reactivity of the polymer because the tighter structure decreases the diffusion of chemical species throughout the polymer. It also decreases the ability of the polymer to swell when placed in a solvent which further

10 improves its chemical resistance. Improvements in such chemical properties are particularly advantageous when the polymer is used to produce ion-exchange membranes. Such membranes must have high resistance to the chemical environments in which they are used, for example in

15 electrochemical cells. However the alteration in the physical and chemical characteristics of the polymer, whilst advantageous for the reasons given above, would be expected to make the polymer more resistant to the grafting of other monomer species to the polymer.

20 Grafting processes known in the art do not effect cross-linking of the polymer and would not be expected to achieve the stated aims of a uniform graft of a monomer throughout a cross-linked polymer within a reasonable

25 reaction time at a low reaction temperature because of the nature of such a polymer.

Thus the present invention provides a process for the preparation of a monomer-grafted cross-linked polymer comprising the steps of:

30

- (i) activating the polymer by irradiation,
 - (ii) quenching the activated polymer so as to effect cross-linking therein,
 - (iii) activating the cross-linked polymer by
- 35 irradiation,

- 6 -

- (iv) contacting the activated cross-linked polymer with an emulsion which comprises
- (a) an unsaturated monomer,
 - (b) an emulsifier, and
 - (c) water,
- for a time sufficient to effect the desired extent of grafting.

The process of the present invention may be used to graft unsaturated monomers to a large number of polymers, copolymers or terpolymers formed from hydrocarbon, halogenated or perhalogenated (in particular fluorinated or perfluorinated) monomers. Preferably the polymer is selected from polyethylene (PE), polytetrafluoroethylene (PTFE), polyhexafluoropropylene (HFP), tetrafluoroethylene-hexafluoropropylene copolymer (FEP), tetrafluoroethylene-propylene copolymer, tetrafluoroethylene-ethylene copolymer (ETFE), hexafluoropropylene-propylene copolymer, hexafluoropropylene-ethylene copolymer, polyvinylidene fluoride (PVDF), vinylidene fluoride tetrafluoroethylene copolymer (PVDF-TFE), vinylidene fluoride hexafluoropropylene copolymer (PVDF-HFP or "Kynar-Flex"), polyvinyl fluoride, tetrafluoroethylene-perfluoroalkyl vinyl ether copolymer, polyvinylidene-hexafluoropropylene copolymer, chlorotrifluoroethylene-ethylene copolymer, chlorotrifluoroethylene-propylene copolymer, perfluoroalkoxy copolymer, polychloroethylene, polyvinyl fluoride, tetrafluoroethylene-perfluoroalkyl vinyl ether copolymer, or perfluoroalkoxy copolymer (PFA). Fluorinated or perfluorinated polymers, copolymers or terpolymers are particularly preferred.

- 7 -

Additionally, the present process may be applied to the grafting of unsaturated monomers to expanded microporous polymers such as expanded PTFE or PVDF.

5 The process of the present invention may be used to graft a large number of unsaturated hydrocarbon, halogenated and perhalogenated monomers. Preferably the unsaturated monomer is selected from styrene, trifluorostyrene, alphas-methylstyrene, alpha,beta-
10 dimethylstyrene, alpha,beta,beta-trimethylstyrene, ortho-methylstyrene, meta-methylstyrene, para-methylstyrene, divinylbenzene, triallylcyanurate, acrylic acid, methacrylic acid, vinylpyrrolidone, vinylpyridine, vinylacetate, trifluorovinylacetate, and
15 methylvinyltoluene and mixtures thereof. It will be noted that some of these monomers are soluble in water, however, the use of an emulsifier as described in the present invention is still advantageous in these cases because it improves the wetting of the polymer.

20 Preferably, the monomer component of the emulsion is present in an amount of from 25 to 70% by weight. More preferably, the monomer component of the emulsion is present in an amount of from 40 to 60% by weight. Even
25 more preferably, the monomer component of the emulsion is present in an amount of from 45 to 55% by weight.

The emulsifier used in the present invention is selected from alkyl sulfates, alkyl aromatic sulfonates,
30 ethoxylated fatty alcohols, fatty acid esters and mixtures thereof. Preferably the emulsifier used is selected from Atlas 3969™ (produced by ICI) or Rhodasurf LA12™ (produced by Rhone Poulenc).

35 Preferably, the emulsifier component of the emulsion is

present in an amount of from 1 to 15% by weight, based on the weight of the monomer. More preferably, the emulsifier component of the emulsion is present in an amount of from 5 to 10% by weight, based on the weight of the monomer. The use of a relatively high concentration of emulsifier improves the wetting of the polymer and also improves emulsion stability.

Preferably the emulsion additionally comprises a coupling agent, such as isopropyl alcohol, which stabilizes the emulsion and enhances wetting.

The emulsion is preferably sparged using nitrogen prior to its use in step (iii) of the process in order to remove oxygen from the mixture which would otherwise react with the radicals formed in the activated polymer to form peroxides. The emulsion produced by the present process is relatively stable which provides an economic advantage in that it can be re-used for numerous graftings. The lower the temperature at which the grafting step is conducted, the more often the emulsion can be re-used. When exhausted the emulsion can be conveniently disposed of by polymerizing the remaining monomer either thermally or by irradiation and filtering out the polymer.

The radiation for activation of the polymer may be provided by gamma rays, X rays, UV light, plasma irradiation or beta particles. Preferably, the radiation used is beta radiation. Beta radiation is preferred for a number of reasons. Firstly the source can be switched on and off as required and secondly, unlike gamma radiation, very high dose rates are possible.

It will be appreciated by those skilled in the art that

- 9 -

the total radiation dose required for the second activation step (step (iii)) depends upon the identity of the base polymer and the bonds contained therein. However, the total radiation dose for the activation step (step iii) is preferably in the range of from 0.1 to 15 Mrad, more preferably from 1 to 10 Mrad. Even more preferably, the radiation dose for step (iii) is in the range of from 6 to 9 Mrad. Preferably, irradiation of the polymer in both steps (i) and (iii) takes place in an inert atmosphere such as nitrogen gas. The radiation dose can be varied to adjust the radical concentration within the polymer to any desired level, the percent graft being dependent upon the activation dose when all other parameters are constant. Thus step (iii) can be used to limit the extent of grafting and if necessary the polymer can be re-irradiated to create more radicals. The polymer will remain activated for up to approximately 2 months if stored at temperatures in the range of from -60 to 0 degC. Consequently, the grafting step need not follow immediately after step (iii). The stability of activated polymers is discussed in US Patent No.4605685.

Preferably, the grafting step (step (iv)) is carried out at a temperature of from 15 to 70°C, more preferably from 45 to 55°C. If other parameters are kept constant, then at lower temperatures the rate of grafting is slower. However, the rate of radical-radical coupling, which reduces the number of available sites for grafting, is also slower and the stability of the emulsion is greater. This leads to a higher overall percentage graft, albeit after a longer reaction time. Slower degradation of the emulsion also means that it can be re-used more often. At higher temperatures the rate of grafting is faster but so too is the rate of

- 10 -

radical-radical coupling and the rate of degradation of the emulsion. This leads to a lower overall percentage graft.

5 The time over which the grafting step takes place may be varied depending upon the desired extent of grafting and on the identity of the polymer and unsaturated monomer involved. However, the grafting step is preferably carried out for a time period in the range of from 0.5
10 to 6 hours, more preferably 2 to 3 hours.

Preferably, the polymer is irradiated in step (i) to within the range of from 10 to 80 Mrad, more preferably 30 to 50Mrad. Preferably, the polymer is quenched in
15 step (ii) by heating in an oxygen free atmosphere, preferably nitrogen, for a time sufficient to effect cross-linking. In this case, the temperature for step (ii) may be in the range of from 50 to 100°C, and preferably approximately 80°C. The time-period for
20 heating is preferably approximately 24 hours. In another embodiment, step (ii) may further involve the use of cross-linking agents. Cross-linking agents may comprise two or more vinyl groups and examples include divinylbenzene and triallyl cyanurate.

25 It has been found that the use of the present process provides high rates of grafting even for these cross-linked polymers. Methods known in the art must usually be practised on uncross-linked polymers because the rate
30 of grafting is prohibitively slow for cross-linked polymers.

In another preferred embodiment of the present invention nitrogen is continuously bubbled through the reaction
35 mixture during the grafting step (step (iv)). This is

- 11 -

particularly advantageous because the turbulence prevents layering of the emulsion and therefore results in a more uniform graft of the monomer to the polymer.

5 In another preferred embodiment of the present invention the pH of the emulsion is adjusted to a value in the range of from 6 to 10, more preferably from 7 to 10.

10 Preferably, the polymer is in the form of a membrane suitable for use as an ion-exchange membrane in an electrochemical cell. In the case where the monomer-grafted polymer is to be made suitable for use as a cation exchange membrane in an electrochemical cell the process preferably additionally comprises the step of
15 sulfonating the monomer-grafted polymer. This provides a membrane which is selective to cations. Preferably, the sulfonation step comprises contacting the monomer-grafted polymer with a mixture of methylene chloride and chlorosulfonic acid.

20 The present invention is illustrated, but not limited, by the typical procedure described below:

A polymer film is cut to a suitable size and placed in
25 a thin plastic bag. The bag is purged with nitrogen several times, then flattened and sealed. The film is irradiated to a dose of from 10 to 70 Mrad then heated to about 80°C for 24 hours. The quenched film is again irradiated to provide the activation dose, typically
30 from 1 to 10 Mrad. The film may then be stored at low temperature, typically from -60 to 0°C, or taken directly on to the grafting step. An emulsion of the monomer may typically be prepared by heating a suitable emulsifier, adding the monomer and slowly adding de-
35 ionised water, the water preferably being at room

- 12 -

temperature, from a squeeze bottle with rapid stirring. On a large scale a homogenizer such as an Eppenbach stirrer may be used to effect emulsification. A typical formula is 5% by weight emulsifier, 47.5% by weight monomer and 47.5% by weight water. The emulsion system is added to a test tube fitted with a ground glass stopper and a nitrogen inlet. The emulsion is sparged for at least two hours then warmed to the desired reaction temperature, typically from 15 to 70°C, in a constant temperature bath. When the emulsion reaches the desired temperature the activated film is inserted into the tube. A mesh is kept on the wall of the tube to prevent the film contacting the glass. After the desired reaction time, typically 0.5 to 6 hours, the film is removed, washed with water and dried to constant weight. The dried film may be sulfonated using a mixture of methylene chloride and chlorosulfonic acid, the chlorosulfonic acid typically being present in a range of from 3 to 5% by weight. The reaction time is about two hours and is best performed in a large sealed test tube. The film is removed, drip-dried and carefully added to cold water. Subsequently the film is heated to about 90°C for about 2 hours to effect hydrolysis. The film may be treated with potassium hydroxide or an emulsifier to lower its resistance. The film is then equilibrated in 0.6 N potassium chloride overnight at about 25°C.

The present invention will now be described with reference to the following specific examples and comparative examples. In the examples the extent of monomer graft to the polymer is expressed by the percentage graft which is calculated using the formula:

$$\text{Percentage graft} = (F_w - I_w) / I_w \times 100$$

- 13 -

 I_w = Initial Weight of Polymer F_w = Final Weight of PolymerComparative Examples 1 to 3

5 Three films; ETFE, 50 μ m thick, PVDF 50 μ m thick and Kynar-Flex (PVDF-HFD copolymer) 85 μ m thick, were cut to 7.6 cm x 10.2 cm and sealed in polyethylene bags. These were irradiated to 9 Mrad (3 passes at 3 Mrad per pass, the films being reversed after each pass). The
10 films were then removed from the bag and immersed in a 7.6 cm long flat-bottom test tube filled with a styrene/toluene mixture (40/60) v/v, which was preheated to 60°C and sparged with nitrogen for 2 hours. The films were separated by Nalgene™ mesh and Nalgene™ mesh was
15 placed on the inner wall of the test tube. The reaction time was 17 hours. The films were removed, dried in air, then heated at 80°C in an oven for 10 minutes. The percentage grafts were:

	1. ETFE	57%
20	2. PVDF	82%
	3. Kynar-flex	17.5%

Examples 4 and 5

A monomer emulsion was prepared by weighing an
25 emulsifier (30.1 gm of Atlas 3969™) into a suitable container and heating gently until the emulsifier just melted. Styrene (301.2 gm) was added and the two components were mixed thoroughly. De-ionised water (334.7 gm) was added from a squirt bottle slowly with stirring.
30 Two films; ETFE 50 μ m thick and Kynar-Flex 85 μ m thick were cut to 7.6 cm x 10.2 cm and sealed in polyethylene bags. They were irradiated to 30 Mrad and quenched at 80°C in nitrogen. They were then irradiated to 9 Mrad (3 passes at 3 Mrad per pass, the films being reversed
35 after each pass). The monomer emulsion prepared above

- 14 -

was heated to 60°C and sparged with nitrogen for two hours. The films were then immersed in a 7.6 cm flat-bottom test tube filled with the emulsion. The reaction was continued at 60°C for 4 hours with nitrogen sparging. The films were washed with de-ionised water and dried. The percentage grafts were:

- | | | |
|----|------------|-------|
| 4. | ETFE | 108% |
| 5. | Kynar-Flex | 78.8% |

The distribution of monomer on the grafted films was very uniform.

Examples 6 and 7

Two films; ETFE and Kynar-Flex were cross-linked and grafted under identical conditions as given in Examples 4 and 5 above except that the time was reduced to 1 hour. The percentage grafts were:

- | | | |
|----|------------|-------|
| 6. | ETFE | 108% |
| 7. | Kynar-Flex | 59.5% |

The distribution of monomer on the grafted films were very uniform.

Example 8

A piece of ETFE film, 15.2 cm x 10.2 cm and 50µm thick was irradiated to 30 Mrad and quenched at 80 °C in nitrogen. It was then irradiated to 9 Mrad and immersed in emulsion (prepared as described in examples 4 and 5) at 50°C for 1 hour giving a graft yield of 37%. The resistance of the film was measured as 0.302 ohms/cm² in 0.6 N KCl solution at 25°C and 1kHz AC.

Example 9

The method of example 8 was repeated using a graft time of 4 hours instead of 1 hour giving a graft yield of 159%. The resistance of the film was measured as 0.120 ohms/cm² in 0.6 N KCl solution at 25°C and 1kHz AC.

Examples 10 to 29

Three different monomer emulsions were prepared using the following components (in wt%):

5 Emulsion 1:

Styrene	47.25
Atlas 3969	5.50
Water	47.25

10 Emulsion 2:

Styrene	39.96
Divinylbenzene	4.44
Triallyl Cyanurate	3.60
Atlas 3969	5.5
Water	46.5

15 Emulsion 3:

Styrene	43.00
Divinylbenzene	2.75
Triallyl Cyanurate	2.25
Atlas 3969	5.5
Water	46.5

20

Films of ETFE and Kynar Flex (KF) were cross-linked and grafted according to the conditions given in the tables below:

	Example	10	11	12	13	14	15	16
	Film type	KF	KF	KF	ETFE	ETFE	KF	KF
5	Thickness of film (μm)	8.9	8.9	8.9	5.1	5.1	8.9	8.9
	Film size (cm x cm)	13x 10	13x 10	13x 10	13x 10	13x 10	13x 10	13x 10
10	Activation dose for step (i) (Mrad)	30	50	70	30	50	30	30
15	Activation dose for step (iii) (Mrad)	9	9	9	9	9	9	9
	Emulsion formulation	1	1	1	1	1	1	1
20	Temperature of step (iv) (°C)	60	60	60	60	60	50	50
25	Time for step (iv) (Hrs)	1	1	1	1	1	1	2
	% Graft	67	67	58	72	68	78	91

	Example	17	18	19	20	21	22	23
	Film type	KF	KF	ETFE	ETFE	ETFE	ETFE	KF
5	Thickness of film (μm)	8.9	8.9	5.1	5.1	5.1	5.1	8.9
	Film size (cm x cm)	13x 10	13x 10	13x 10	13x 10	13x 10	13x 10	13x 10
10	Activation dose for step (i) (Mrad)	30	70	30	30	30	30	30
15	Activation dose for step (iii) (Mrad)	9	9	6	6	6	9	9
	Emulsion formulation	1	1	1	1	1	2	2
20	Temperature of step (iv) (°C)	50	50	55	55	55	50	50
25	Time for step (iv) (Hrs)	3	1	2	1	0.5	16	2
	% Graft	114	87	150	100	40	181	15

	Example	24	25	26	27	28	29
	Film type	KF	KF	KF	KF	KF	KF
5	Thickness of film (μm)	8.9	8.9	8.9	8.9	8.9	8.9
	Film size (cm x cm)	13x 10	13x 10	13x 10	13x 10	13x 10	13x 10
10	Activation dose for step (i) (Mrad)	30	30	30	30	30	30
15	Activation dose for step (iii) (Mrad)	6	9	9	9	9	9
	Emulsion formulation	2	2	3	3	2	2
20	Temperature of step (iv) ($^{\circ}\text{C}$)	50	50	50	50	50	50
25	Time for step (iv) (Hrs)	3	5.5	2	2	2	2
	% Graft	33	40	24	25	48	37

- 19 -

The present invention as described above provides a process for the preparation of a monomer-grafted cross-linked polymer which has a number of significant advantages. The process provides high percentage grafts in a much shorter reaction time and at lower reaction temperatures than conventional processes which use an organic solvent even though the polymer is cross-linked and even with hydrophobic polymers such as the preferred fluorinated polymers. The high speed of the reaction enables grafting to cross-linked polymers which usually react too slowly to be viable. As well as obvious cost savings, the speed of the grafting reaction and the low temperature at which it may be performed consequently confer a number of advantages on the process. The use of low temperatures alleviates the problem of homopolymerization due to thermal activation. At a reaction temperature of 40 to 45°C no homopolymer is evident in the grafting emulsion or grafted polymer even after 4 or 5 graft cycles using the same monomer emulsion. Cross-linking monomers, for example divinylbenzene and triallylcyanurate, can also be added to the emulsion without causing gelation. It also allows the process to be performed in a continuous manufacturing line rather than in batches. The low temperature and short reaction time combined with the stability of the emulsion allow for a continuous grafting process on a pre-irradiated film providing low cost manufacturing possibilities. The present process provides extremely high quality cross-linked and grafted polymers in terms of the uniformity of the graft throughout the polymer. The use of the post-irradiation grafting technique eliminates homopolymerization due to irradiation of the monomer. The elimination of homopolymerization allows the use of high concentrations of monomers and/or difunctional monomers. The water

present in the emulsion is advantageous in moderating the heat of reaction due to its high specific heat capacity. This reduces the need to cool the reaction. It is believed that the radical inhibitors present in the commercially available monomers are partitioned into the water phase. This obviates the need for the removal of radical inhibitors prior to grafting. The emulsion is stable and may be re-used a number of times decreasing the waste per unit of production. The extent of re-use is dependent upon the reaction time and the reaction temperature for the grafting step. The stability of the emulsion allows it to be stored at room temperature, the volatility and toxicity of the organic solvents used in known processes makes storage of monomer solutions problematic. Waste emulsion can be conveniently disposed of by heating with an initiator to polymerize the remaining monomer. This can be filtered, heated further to ensure complete elimination of the monomer and discarded. A further benefit is that no organic solvent is required. This provides advantages in terms of cost, safety and the environment. By cross-linking the polymer prior to grafting the process further provides polymers with advantageous physical and chemical properties, these properties being especially favoured when the polymer is used to form ion-exchange membranes.

Claims

1. A process for the preparation of a monomer-grafted cross-linked polymer comprising the steps of:
 - (i) activating the polymer by irradiation,
 - (ii) quenching the activated polymer so as to effect cross-linking therein,
 - (iii) activating the cross-linked polymer by irradiation,
 - (iv) contacting the activated cross-linked polymer with an emulsion which comprises
 - (a) an unsaturated monomer,
 - (b) an emulsifier, and
 - (c) water,for a time sufficient to effect the desired extent of grafting.
2. A process according to claim 1 wherein the polymer is selected from the group consisting of fluorinated and perfluorinated polymers, copolymers and terpolymers.
3. A process according to claim 1 wherein the polymer is selected from the group consisting of polyethylene, polytetrafluoroethylene, polyhexafluoropropylene, tetrafluoroethylene-hexafluoropropylene copolymer, tetrafluoroethylene-propylene copolymer, tetrafluoroethylene-ethylene copolymer, hexafluoropropylene-propylene copolymer, hexafluoropropylene-ethylene copolymer, polyvinylidene fluoride, vinylidene fluoride tetrafluoroethylene copolymer, vinylidene fluoride hexafluoropropylene copolymer, polyvinyl fluoride, tetrafluoroethylene-perfluoroalkyl vinyl ether copolymer, polyvinylidene-hexafluoropropylene

- 22 -

5 copolymer, chlorotrifluoroethylene-ethylene
copolymer, chlorotrifluoroethylene-propylene
copolymer, perfluoroalkoxy copolymer,
polychloroethylene, polyvinyl fluoride,
tetrafluoroethylene-perfluoroalkyl vinyl ether
copolymer, and perfluoroalkoxy copolymer.

10 4. A process according to claim 1 wherein the
unsaturated monomer is selected from the group
consisting of styrene, trifluorostyrene,
alphamethylstyrene, alpha,beta-dimethylstyrene,
alpha,beta,beta-trimethylstyrene, ortho-
methylstyrene, meta-methylstyrene, para-
methylstyrene, divinylbenzene, triallylcyanurate,
15 acrylic acid, methacrylic acid, vinylpyrrolidone,
vinylpyridine, vinylacetate, trifluorovinylacetate,
and methylvinyltoluene, and mixtures thereof.

20 5. A process according to claim 1 wherein the monomer
component of the emulsion is present in an amount
of from 25 to 70% by weight.

25 6. A process according to claim 1 wherein the monomer
component of the emulsion is present in an amount
of from 40 to 60% by weight.

30 7. A process according to claim 1 wherein the monomer
component of the emulsion is present in an amount
of from 45 to 55% by weight.

8. A process according to claim 1 wherein the
emulsifier is selected from alkyl sulfates, alkyl
aromatic sulfonates, ethoxylated fatty alcohols,
fatty acid esters or mixtures thereof.

35

9. A process according to claim 1 wherein the emulsifier component of the emulsion is present in an amount of from 1 to 15% by weight, based on the weight of the monomer.
- 5
10. A process according to claim 1 wherein the emulsifier component of the emulsion is present in an amount of from 5 to 10% by weight, based on the weight of the monomer.
- 10
11. A process according to claim 1 wherein the emulsion is prepared by a process which comprises the steps of:
- 15
- (a) heating the emulsifier until it just melts,
 - (b) adding the monomer,
 - (c) adding the water with stirring.
12. A process according to claim 1 wherein the emulsion additionally comprises isopropyl alcohol.
- 20
13. A process according to claim 1 wherein the total radiation dose for step (iii) is in the range of from 1 to 10 Mrad.
- 25
14. A process according to claim 1 wherein the total radiation dose for step (iii) is in the range of from 6 to 9 Mrad.
- 30
15. A process according to claim 1 wherein the radiation for steps (i) and (iii) is provided by gamma rays, X rays, UV radiation, plasma irradiation or beta particles.
- 35
16. A process according to claim 1 wherein step (iv) is

carried out at a temperature in the range of from 15 to 70°C.

- 5 17. A process according to claim 1 wherein step (iv) is carried out at a temperature in the range of from 45 to 55°C.
- 10 18. A process according to claim 1 wherein step (iv) is carried out for a time period in the range of from 0.5 to 6 hours.
- 15 19. A process according to claim 1 wherein step (iv) is carried out for a time period in the range of from 2 to 3 hours.
- 20 20. A process according to claim 1 wherein the total radiation dose for step (i) is in the range of from 10 to 80 Mrad.
- 25 21. A process according to claim 1 wherein step (ii) comprises heating in an oxygen free atmosphere.
22. A process according to claim 1 wherein step (ii) comprises adding one or more cross-linking agents.
- 30 23. A process according to claim 21 wherein the one or more cross-linking agents are selected from divinylbenzene and triallyl cyanurate.
24. A process according to claim 1 wherein nitrogen is continuously bubbled through the reaction mixture during step (iii).
- 35 25. A process according to claim 1 additionally comprising the step of sulfonating the monomer-

- 25 -

grafted cross-linked polymer.

- 5 26. A process according to claim 25 wherein the sulfonation step comprises contacting the monomer-grafted cross-linked polymer with a mixture of methylene chloride and chlorosulfonic acid.
- 10 27. A process as claimed in claim 1 wherein the polymer is in the form of a membrane suitable for use in an electrochemical cell.
28. A process as claimed in claim 1 wherein the polymer is an expanded microporous polymer structure.
- 15 29. A process as claimed in claim 1 wherein the polymer is in a form selected from the group consisting of threads, non-woven fabrics, tubes, powders, pellets, sheets and films.
- 20 30. A monomer-grafted cross-linked polymer whenever produced by the process as claimed in claim 1 or claim 25.
- 25 31. An ion-exchange membrane for use in an electrochemical cell which comprises a monomer-grafted cross-linked polymer as claimed in claim 30.

INTERNATIONAL SEARCH REPORT

International Application No
PCT/GB 99/02868

A. CLASSIFICATION OF SUBJECT MATTER
IPC 7 C08F291/18 B01D67/00 C08F259/08 C08F259/02 C08F255/02

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 7 C08F B01D B01J C08L C08J H01M

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 4 407 846 A (MACHI SUEO ET AL) 4 October 1983 (1983-10-04)	1,3-7, 13, 15-21, 27-31
Y	* column 2, line 11-19 * column 2, line 33-39; claims 1-4; examples 1-4	2
X	EP 0 526 203 A (TONEN SEKIYUKAGAKU KK) 3 February 1993 (1993-02-03)	1,3-11, 13-21, 27-31
Y	the whole document	22-24

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- "&" document member of the same patent family

Date of the actual completion of the international search

26 October 1999

Date of mailing of the international search report

03/11/1999

Name and mailing address of the ISA
European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer


Hammond, A

INTERNATIONAL SEARCH REPORT

Inter- national Application No
PCT/GB 99/02868

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 3 481 848 A (GOTOHDA MASAO ET AL) 2 December 1969 (1969-12-02) * column 1, line 44-49 ; example 6 * claims 1-5; examples 1-5 ---	1,3,4, 8-11,13, 15-19, 21,24, 27-31
X	US 5 743 940 A (SEKIGUCHI HIDEAKI ET AL) 28 April 1998 (1998-04-28) * claim 10 ; example 7 * abstract; claims 8,9; example 1 ---	1-5, 8-11,15, 16,18, 20,21, 24-31 13,14,19
Y	US 5 164 424 A (BRUESCHKE HARTMUT E A ET AL) 17 November 1992 (1992-11-17) * abstract ; column 5, line 28 - column 6, line 6 * column 7, line 49 -column 10, line 2; example 1 ---	13,14,19
Y	US 4 602 045 A (MARKUS MICHAEL V ET AL) 22 July 1986 (1986-07-22) column 3, line 35 -column 4, line 16 ---	2
Y	US 4 652 592 A (KAWASHIMA CHIKASHI ET AL) 24 March 1987 (1987-03-24) column 1, line 16-24; claims 1-12 ---	22-24
A	US 5 652 281 A (GALLI PAOLO ET AL) 29 July 1997 (1997-07-29) claims 1-11 -----	1-31



INTERNATIONAL SEARCH REPORT

information on patent family members

International Application No

PCT/GB 99/02868

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 4407846 A	04-10-1983	JP 1442762 C JP 55106239 A JP 62047896 B	08-06-1988 14-08-1980 09-10-1987
EP 0526203 A	03-02-1993	JP 2725094 B JP 5031343 A DE 69203172 D DE 69203172 T	09-03-1998 09-02-1993 03-08-1995 09-11-1995
US 3481848 A	02-12-1969	NONE	
US 5743940 A	28-04-1998	JP 1258740 A JP 1893229 C JP 6020554 B DE 3910874 A	16-10-1989 26-12-1994 23-03-1994 19-10-1989
US 5164424 A	17-11-1992	DE 3643574 A AT 87942 T DE 3785361 A WO 8804677 A EP 0338004 A JP 7086126 B JP 2501659 T	30-06-1988 15-04-1993 13-05-1993 30-06-1988 25-10-1989 20-09-1995 07-06-1990
US 4602045 A	22-07-1986	WO 8201882 A EP 0065547 A JP 2061498 B JP 57501858 T ZA 8108207 A	10-06-1982 01-12-1982 20-12-1990 14-10-1982 27-10-1982
US 4652592 A	24-03-1987	JP 1505731 C JP 61023638 A JP 63052044 B DE 3524370 A FR 2567528 A GB 2161816 A, B IT 1206737 B	13-07-1989 01-02-1986 17-10-1988 16-01-1986 17-01-1986 22-01-1986 03-05-1989
US 5652281 A	29-07-1997	US 5411994 A AT 118792 T AU 630534 B AU 6825790 A CA 2031406 A CN 1054077 A, B DE 69017184 D DE 69017184 T DK 437808 T EP 0437808 A FI 906310 A JP 6157683 A PT 96292 A, B RU 2090574 C	02-05-1995 15-03-1995 29-10-1992 27-06-1991 22-06-1991 28-08-1991 30-03-1995 29-06-1995 19-06-1995 24-07-1991 22-06-1991 07-06-1994 30-09-1995 20-09-1997

INTERNATIONAL SEARCH REPORT

International Application No.

PCT/EP 03/06580

A. CLASSIFICATION OF SUBJECT MATTER
IPC 7 H01M8/10

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 H01M

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 6 242 123 B1 (ITO NAOKI ET AL) 5 June 2001 (2001-06-05) claims 1-31	1-52
A	US 5 679 482 A (EHRENBERG SCOTT G ET AL) 21 October 1997 (1997-10-21) claims 1-25	1-52
A	US 6 268 430 B1 (CHOI SUSAN KUHARCIK ET AL) 31 July 2001 (2001-07-31) claims 1-16	1-52
A	US 4 287 032 A (PELLEGRI ALBERTO) 1 September 1981 (1981-09-01) claims 1-17	1-52

☐ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
- *G* document member of the same patent family

Date of the actual completion of the international search

5 February 2004

Date of mailing of the international search report

12/02/2004

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Battistig, M

INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 03/06580

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 6242123	B1	05-06-2001	JP 11111310 A DE 19844645 A1 GB 2330836 A ,B	23-04-1999 01-04-1999 05-05-1999
US 5679482	A	21-10-1997	US 5468574 A AU 2644395 A BR 9507759 A CA 2190848 A1 CN 1152929 A DE 69519855 D1 DE 69519855 T2 EP 0763070 A1 JP 10503788 T WO 9532236 A1	21-11-1995 18-12-1995 23-09-1997 30-11-1995 25-06-1997 15-02-2001 02-08-2001 19-03-1997 07-04-1998 30-11-1995
US 6268430	B1	31-07-2001	US 6100324 A AU 3645599 A CA 2326845 A1 CN 1297457 T EP 1082358 A1 JP 2002511502 T WO 9952954 A1	08-08-2000 01-11-1999 21-10-1999 30-05-2001 14-03-2001 16-04-2002 21-10-1999
US 4287032	A	01-09-1981	IT 1122385 B DE 3028931 A1 FR 2463200 A1 GB 2060703 A ,B JP 1183970 C JP 56033489 A JP 58015549 B	23-04-1986 19-02-1981 20-02-1981 07-05-1981 27-12-1983 03-04-1981 26-03-1983

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☐ FADED TEXT OR DRAWING
- ☒ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☐ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.

THIS PAGE BLANK (USPTO)